

## Microwave synthesis of $\text{YFeO}_3$

E. V. Tomina, Yu. N. Gudkova, Yu. A. Belashkova, N. I. Boykov  
Voronezh State University, Voronezh, Russia,  
e-mail: gudkova.yuliya1994@mail.ru

Microwave radiation acting directly on the reaction mixture leads to higher rate of the chemical reaction as compared with the thermal heating. Sodium hydroxide NaOH (20 %, analytical grade, Russian State Standard GOST 432877), yttrium nitrate  $\text{Y}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$  (analytical grade, CAS 13494-98) and iron nitrate (III)  $\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$  (pure, TU 6-09-02-553-96) were used as precursors for the synthesis of  $\text{YFeO}_3$ .

The reaction of yttrium ferrite precipitating was carried out under microwave irradiation on the precursors solution at 700 W during 26 min. After cooling to room temperature, yttrium ferrite precipitate was separated from the solution by filtration, air dried and annealed in a muffle oven for two hours at 800 °C. According to the XRD the sample is almost pure  $\text{YFeO}_3$  with minor inclusions of  $\text{Y}_2\text{O}_3$  and  $\text{Fe}_2\text{O}_3$ . The average particle size is about 40 nm.




Fig. The diffractogram of  $\text{YFeO}_3$ , synthesized under microwave irradiation.

**Acknowledgment.** This work was supported by the Ministry of Education and Science of the Russian Federation in line with government order for Higher Education Institutions in the field of science for 2014-2016 years (project N 225).